Helmholtz-Zentrum Dresden-Rossendorf (HZDR)



Mechanisms of selenium removal by partially oxidized magnetite nanoparticles for waste water remediation

Börsig, N.; Scheinost, A.; Schild, D.; Neumann, T.;

Originally published:

July 2021

Applied Geochemistry 132(2021), 105062

DOI: https://doi.org/10.1016/j.apgeochem.2021.105062

Perma-Link to Publication Repository of HZDR:

https://www.hzdr.de/publications/Publ-30871

Release of the secondary publication on the basis of the German Copyright Law § 38 Section 4.

CC BY-NC-ND

1	MANUSCRIPT
2	Selenite and selenate adsorption mechanisms on
3	partially oxidized magnetite nanoparticles

- 4 Nicolas Börsig ^{a,*}, Andreas C. Scheinost ^{b,c}, Dieter Schild ^d, Thomas Neumann ^e
- ^a Karlsruhe Institute of Technology (KIT), Institute of Applied Geosciences, Adenauerring 20b,
 76131 Karlsruhe, Germany
- ^b Helmholtz-Zentrum Dresden-Rossendorf (HZDR), Institute of Resource Ecology, Bautzner
 Landstraße 400, 01328 Dresden, Germany
- ^c The Rossendorf Beamline (ROBL) at ESRF, 38043 Grenoble, France
- ^d Karlsruhe Institute of Technology (KIT), Institute for Nuclear Waste Disposal,
- 11 Hermann-von-Helmholtz-Platz 1, 76344 Eggenstein-Leopoldshafen, Germany
- ^e Technische Universität Berlin, Institute of Applied Geosciences, Ernst-Reuter-Platz 1, 10587 Berlin,
 Germany
- 14 *Corresponding author: Tel.: +49 721 608-44878; nicolas.boersig@kit.edu (N. Börsig)
- Keywords: selenium, oxyanions, Se(IV), Se(VI), iron oxides, maghemite, immobilization,
 retention, remediation, XPS, XAFS, XANES, EXAFS

17 Environmental Significance Statement (max. 120 words)

18 Affordable and easy-to-produce nanoparticles are widely used in wastewater treatment 19 applications. The mixed-valence iron oxide mineral magnetite has emerged as suitable material 20 for the remediation of contaminated wastewaters due to its magnetic properties and high 21 reactivity. Since the physicochemical properties of magnetite are strongly influenced by 22 oxidation, however, the retention behavior of nanoparticulate magnetite can change 23 substantially in natural environments. In this study, we explore the retention efficiency and 24 capacity of partially oxidized magnetite nanoparticles with respect to dissolved selenium 25 oxyanions and illustrate the effective adsorption mechanisms. The obtained results significantly 26 contribute to the understanding of the retention behavior of selenium oxyanions in contact with 27 nanoparticulate magnetite/maghemite phases in oxic environments typical for waste water 28 treatment.

29

30 Abstract

31 Magnetite nanoparticles are a promising cost-effective material for the remediation of polluted 32 wastewaters. Due to their magnetic properties and their high adsorption and reduction potential, 33 they are particularly suitable for the decontamination of oxyanion-forming contaminants, including the highly mobile selenium oxyanions selenite and selenate. However, little is known 34 35 how in field applications the remediation efficiency of magnetite nanoparticles is affected by 36 partial oxidation and the formation of magnetite/maghemite phases. Here we characterize the 37 retention mechanisms and capacity of partially oxidized nanoparticulate magnetite for selenite 38 and selenate at different pH conditions and ionic strengths. Selenate was retained only under 39 acidic conditions and strongly influenced by competing chloride anions, indicative of outer-40 sphere adsorption. Although the adsorption of selenite was also adversely affected by increasing 41 pH, substantial quantities were retained even at alkaline conditions. Using spectroscopic 42 analyses (XPS, XAFS), both mononuclear edge-sharing (^{2}E) and binuclear corner-sharing (^{2}C) 43 inner-sphere selenite surface complexes could be identified, while reduction to Se(0) or Se(-II) 44 species could be excluded. Under favorable adsorption conditions up to pH \sim 8, the affinity of 45 selenite to form ²C surface complexes is higher, whereas at alkaline pH values and less 46 favorable adsorption conditions ²E complexes prevail. Our results demonstrate that magnetite 47 can be used as a suitable reactant for the immobilization of selenium as selenite in remedial 48 applications, even under oxic conditions and without the involvement of reduction processes.

49 Graphical abstract

50 This article provides new insights into the retention behavior of partially oxidized magnetite 51 nanoparticles in contact with selenium oxyanions under oxic conditions



52

Partially oxidized magnetite nanoparticles

53 1 Introduction

54 Selenium (Se) pollution of soils, sediments and waters is a global phenomenon. Although Se is 55 a naturally occurring trace element, the major cause of Se release and contamination are human 56 activities such as coal production and combustion, phosphate and sulfide-ore mining, metal 57 processing, oil refining, waste disposal or agricultural irrigation (Dhillon and Dhillon, 2003; 58 Lemly, 2004; Tan et al., 2016). Additionally, Se occurs in vitrified high-level nuclear waste 59 (HLW) in the form of the long-lived, harmful radionuclide 79 Se and plays a major role in the 60 long-term safety assessment of HLW repositories (Frechou et al., 2007; De Cannière et al., 61 2010; Bingham et al., 2011).

62 In aquatic systems, Se levels can rapidly become toxic endangering not only the health of 63 aquatic organisms but also of other beings, including humans, due to bioaccumulation in the 64 food chain (Munier-Lamy et al., 2007; Lenz and Lens, 2009). Mobility and bioavailability of 65 Se in water is mainly controlled by its solubility and retention through (bio)chemical processes (Dhillon and Dhillon, 2003; Fernández-Martínez and Charlet, 2009), which are largely 66 67 determined by the prevailing Se oxidation state and related chemical speciation. Under reducing 68 conditions, Se forms sparingly soluble minerals and compounds, primarily elemental selenium 69 (Se^{0}) and metal selenides (Se(-I) and Se(-II)) (ESI Fig. A.1). Under (sub)oxic conditions, 70 however, inorganic Se occurs in the oxidation state Se(IV) and Se(VI) as highly soluble and 71 mobile oxyanions selenite (SeO $_3^{2-}$) and selenate (SeO $_4^{2-}$). Both selenite and selenate form 72 protonated and deprotonated species depending on the solution pH (Fig. 1).

73 A key factor controlling the fate of dissolved Se oxyanions in aquatic environments is sorption 74 on geological materials. Of special relevance in this context are metal (hydr)oxides and 75 particularly iron (hydr)oxides due to their high affinity towards oxyanion-forming pollutants 76 such as Se, As, Sb, V, Mo or Cr (Chan et al., 2009; Nakamaru and Altansuvd, 2014; Börsig et 77 al., 2017; Weidner and Ciesielczyk, 2019). Besides adsorption, reduction of oxyanions to less soluble compounds is an important abiotic immobilization process (Wilkin et al., 2005; Kirsch 78 79 et al., 2008; Scheinost et al., 2008), driven by Fe^0 or by Fe(II)-bearing iron (hydr)oxides, yet 80 depends strongly on the prevailing redox conditions.



81

Fig. 1: (Left) Eh-pH diagram for the system Se-H₂O at 25°C and 1 atm; Setotal: 10⁻⁶ mol/L. (Right) Stability and distribution of dissolved Se(-II), Se(VI), and Se(VI) species as a function of pH. Diagrams were calculated with PHREEQC (USGS) using an adapted *wateq4f* database; thermodynamic Se data: aquatic species (Séby et al., 2001), solid phases (Salah and Wang, 2014).

86 Magnetite [Fe₃O₄] is one of the most widespread iron (hydr)oxide minerals in nature and is also 87 known as a sink for dissolved oxyanions due to its high adsorption and reduction potential. Due 88 to these properties and its magnetic character, which permits an easy separation of magnetite 89 and associated contaminants from the waste water stream, the use of magnetite is considered in 90 various in-situ and ex-situ environmental remediation approaches, including wastewater treatment or soil remediation (Kuppusamy et al., 2016; Usman et al., 2018). Particularly for 91 92 decontamination of wastewaters based on the removal of hazardous oxyanions by nano-93 remediation, nanoparticulate magnetite is a promising cost-effective material (Chowdhury and 94 Yanful, 2010; Horst et al., 2015; Li et al., 2017), as shown by several previous studies (Martínez 95 et al., 2006; Scheinost and Charlet, 2008; Loyo et al., 2008; Jordan et al., 2009; Missana et al., 2009; Usman et al., 2018). 96

97 For field applications, however, it must be taken into account that reactivity and capacity of a 98 remediation material is highly dependent on its stability under various environmental 99 conditions. This applies in particularly for redox- and pH-sensitive minerals such as magnetite 100 and other reduced or mixed-valent iron minerals like zerovalent iron (ZVI) and green rust 101 (Génin et al., 2006; Liu et al., 2014; Mu et al., 2017; Börsig et al., 2018). A common 102 phenomenon for magnetite is thereby the transformation into maghemite $[\gamma-Fe_2O_3]$ under oxic 103 conditions (ESI Fig. A.1) due to surface oxidation (Rebodos and Vikesland, 2010; 104 Schwaminger et al., 2017).

105

$$2 F e^{II} F e_2^{III} O_4 + 0.5 O_2 \rightarrow 3 \gamma F e_2^{III} O_3$$

106 Maghemite is the Fe(II)-free oxidation product of magnetite and both minerals represent the 107 end members of a solid solution series (Iwatsuki and Fukasawa, 1993; Gorski and Scherer, 108 **2010**. In case of larger magnetite crystals, oxidation of the mineral surface can result in the 109 formation of a passivating layer of maghemite that protects the underlying magnetite from 110 further oxidation (He and Traina, 2005; Rebodos and Vikesland, 2010; Khan et al., 2015). By 111 contrast, magnetite nanoparticles produced by chemical synthesis usually consist of both 112 magnetite and maghemite with a higher proportion of maghemite in the near-surface region 113 (Kuhn et al., 2002; Signorini et al., 2003; Sharifi Dehsari et al., 2018).

114 In order to assess the efficiency of magnetite for remediation measures, it is therefore important 115 to know to what extent oxidation and formation of a mixed magnetite/maghemite phase affects 116 the retention of pollutants, particularly in terms of the specific mechanisms. The aim of this 117 paper was therefore to characterize the retention efficiency of partially oxidized magnetite with 118 respect to dissolved Se oxyanions. For this, we examined the interaction of selenite and selenate 119 with pre-oxidized magnetite in adsorption experiments at various hydrochemical conditions, 120 including pH and ionic strength. By using hydrochemical data and a combination of solids 121 analysis, we were able to determine the Se retention capacity and stability as well as the 122 involved immobilization mechanisms.

123 2 Materials and Methods

124 **2.1** Synthesis of magnetite

125 Magnetite (Mt) was synthesized in the laboratory by progressively oxidizing an aquatic Fe^{2+} 126 solution under alkaline pH conditions (ESI Fig. A.2). A detailed description of the synthesis 127 procedure, the sample preparation as well as of the characterization of the final product can be 128 found in Börsig et al. (2018). In short, 5 g FeCl₂ \cdot 4 H₂O were dissolved in 500 ml N₂-degassed 129 Milli-Q water. After adding 55 mL 1 M KOH and 25 mL 1 M NaHCO₃ solution, blueish green 130 colored iron(II) hydroxide precipitated. Continuous stirring resulted in the progressive 131 oxidation of the initial anoxic system by atmospheric oxygen, causing the transformation of 132 iron(II) hydroxide into black magnetite within 48 hours. With approximately 2 g of magnetite 133 formed, the mass to volume ratio (m/V) during synthesis was about 3.4 g/L and the final pH 134 was around 9.2. After synthesis, the magnetite phase was decanted, centrifuged and washed 135 three times with Milli-Q water. After drying at 40°C, the synthesized particles were ground 136 with an agate mortar and stored for analysis and adsorption experiments.

137 XRD analysis of the synthesis product proved the formation of magnetite $[Fe_3O_4]$ without any 138 indication of additional iron (hydr)oxide phases. According to SEM characterization, the 139 magnetite consisted of aggregated particles with a single-particle size of about 50 nm. A 140 specific surface area of $32 \text{ m}^2/\text{g}$ was determined by BET analysis, consistent with literature 141 values (Cornell and Schwertmann, 2003; Salazar Camacho and Villalobos Peñalosa, 2017). 142 XPS analysis and the evaluation of the Fe $2p_{3/2}$ spectra, however, showed that the Fe(II) to 143 Fe_{total} ratio was only 0.14 ($\pm 5\%$) at the surface and therefore lower than the expected ratio of 144 0.33 for stoichiometric Fe₃O₄. Note that the information depth of the Fe $2p_{3/2}$ elemental line of 145 magnetite was calculated with 2.2 nm (see ESI). This indicated that the synthesized magnetite 146 was partially oxidized and that the near-surface region of these particles may consist of both 147 magnetite and maghemite.

148 **2.2** Adsorption experiments

149 Adsorption of selenite and selenate with this pre-oxidized magnetite was studied in batch 150 experiments under oxic conditions. The experimental setup was almost identical to the 151 conditions at the end of the magnetite synthesis. To investigate selenite and selenate adsorption 152 as a function of the Se concentrations, 50 ml 0.01 M KCl solution that contained distinct 153 volumes of Se stock solution was added to 170.0 mg of washed magnetite powder (m/V ratio 154 = 3.4 g/L). The Se stock solutions were prepared by dissolving defined quantities of Na₂SeO₃ 155 or Na₂SeO₄· 10 H₂O in N₂-degassed Milli-Q water. The added volumes were calculated to obtain initial selenite or selenate concentrations of 10⁻⁵ - 10⁻² mol/L. KCl was used as 156 157 background electrolyte since also the original synthesis took place in such conditions and to 158 simulate solutions with higher ionic strengths. After mixing, the pH was adjusted to 9.2 by 159 dropwise addition of KOH solution. The 50 mL flasks were sealed and shaken for 48 hours to 160 ensure that adsorption equilibrium was achieved. Due to the strong buffer capacity of magnetite, 161 pH was checked after 24 and 45 hours and if necessary readjusted to pH 9.2. Afterwards, the 162 residual Se concentration in solution was analyzed and the solids were dried at 40°C both with 163 and without prior washing.

In addition, similar batch experiments were carried out to study the influence of pH and ionic strength. While selenite or selenate concentration was kept constant (10^{-4} mol/L), different ionic

strengths of 0.01 M KCl or 0.14 M KCl were tested and pH values were adjusted in the range

167 of 2 to 14 using either HCl or KOH solution.

168 2.3 Analytical techniques

169 Dissolved Se and Fe concentrations were determined by Inductively-Coupled Plasma Optical 170 Emission Spectrometry (ICP-OES; Varian 715ES) or Inductively-Coupled Plasma Mass 171 Spectrometry (ICP-MS; X-Series 2, Thermo Fisher Scientific Inc.) depending on the solution 172 concentrations. X-Ray Diffraction (XRD) for analysis of the mineral composition was 173 performed on a Bruker D8 Advance X-ray diffractometer (Cu Kα). The total Se content of the 174 solid phases was determined by polarized Energy Dispersive X-ray Fluorescence Spectroscopy 175 (pEDXRF) with an Epsilon 5 (PANalytical). Electron microscopy with Energy Dispersive X-176 ray Spectroscopy (EDX) was used to characterize the solid phases. Images were recorded using 177 a LEO 1530 (Zeiss Inc.) Scanning Electron Microscope (SEM) with a NORAN System SIX 178 (Thermo Electron Corp.) EDX-System. To examine oxidation states and to identify elemental 179 composition of the surface area, X-ray Photoelectron Spectroscopy (XPS) measurements were 180 performed using a PHI 5000 VersaProbe II (ULVAC-PHI, Inc.). Detailed information about 181 measurement parameters, sample preparation and data evaluation are described in the **ESI**.

182 X-ray absorption spectroscopy was carried out on selected samples to identify the Se oxidation 183 state, coordination as well as the molecular short-range structure. Se K-edge X-ray Absorption 184 Fine Structure (XAFS) spectra were collected at The Rossendorf Beamline (ROBL) at ESRF 185 (Grenoble, France). Measurement parameters and sample preparation are described in detail in 186 the **ESI**. Fluorescence deadtime correction, energy calibration and averaging of scans was 187 performed with the software package SixPack {Webb, 2005 #609}(www.sams-188 xrays.com/sixpack), while normalization and extraction of the EXAFS chi function was 189 performed with the software WinXAS according to standard procedures (Ressler, 1998). The 190 k^3 -weighted EXAFS data were fit using theoretical back-scattering amplitudes and phase shifts 191 calculated with FEFF 8.2 (Ankudinov and Rehr, 1997). Statistical analysis of spectra was performed with the ITFA program package (Rossberg et al., 2003). Spectra of Se reference 192 193 samples were taken from Scheinost and Charlet (2008).

194 **3** Results and Discussion

195 3.1 Adsorption capacity of oxidized magnetite for selenite and selenate

Fig. 2a shows the adsorption capacity of magnetite for selenite and selenate under oxic conditions as a function of pH and ionic strength. The results demonstrate that the adsorption behavior is primarily affected by the Se species. Selenate is only immobilized under extreme acidic conditions, with about 50% of selenite adsorbed at pH 3. Contrary to selenate, the entire

200 initial selenite amount is immobilized at low pH (< pH 5) and the adsorption edge extends over 201 a wide pH range from weakly acidic to alkaline (pH 6–11) conditions. Furthermore, while the 202 adsorption edge of selenate shifts towards lower pH values (~1.5 pH unit) in the presence of 203 higher KCl concentrations, retention of selenite is not affected by higher ionic strengths. Further 204 confirmation for this observation can also be seen in Fig. 2b, which shows the distribution 205 coefficient (K_d) as a function of the selenite equilibrium concentration at pH 9.2. With 206 increasing concentrations of dissolved Se, $\log K_d$ values decrease steadily but are identical for 207 both ionic strengths. The absolute K_d values are furthermore quite high (log K_d: 3.2–1.2 L/kg) 208 and correspond to Se surface coverages in the range of 0.05 to 2.5 at/nm². Unlike selenite, the 209 adsorption of selenate was too low to obtain reliable K_d data at pH 9.2.



210



214 The observed adsorption behavior is consistent with the literature. Adsorption capacities of iron 215 (hydr)oxides for anions such as selenite and selenate decrease with increasing pH as the amount 216 of positively charged surface groups declines by deprotonation. Since in particular the single-217 protonated Se species (HSeO₃⁻ and HSeO₄⁻) interact with the hydroxyl groups on the magnetite 218 surface (Martínez et al., 2006; Kim et al., 2012), the position of the adsorption edges also 219 correlates with the pH-dependent distribution of those species in solution (Fig. 1). However, 220 even at alkaline conditions of pH > 10, where the point of zero charge of magnetite (reported 221 PZC values ranging from 6.5 to 8.1) is already exceeded and the surface is negatively charged 222 (Milonjić et al., 1983; Hu et al., 2010), significant amounts of selenite are adsorbed. 223 Responsible for this immobilization is the specific adsorption of selenite resulting in the

224 formation of inner-sphere surface complexes (Martínez et al., 2006; Loyo et al., 2008; Jordan 225 et al., 2009; Kim et al., 2012). Due to this inner-sphere selenite adsorption, large distribution 226 coefficients as well as high Se surface coverages of up to 2.5 at/nm² can be observed even at 227 pH 9.2. Such values were found not only for magnetite (Kim et al., 2012) but also for hematite 228 and goethite (Su and Suarez, 2000; Duc et al., 2003; Rovira et al., 2008; Börsig et al., 2017). In 229 addition, formation of inner-sphere complexes explains why selenite adsorption is not 230 dependent on the ionic strength. By contrast, selenate primarily forms outer-sphere adsorption 231 complexes in contact with iron (hydr)oxides (Hayes et al., 1987; Rietra et al., 2001; Jordan et 232 al., 2013). This would explain the almost non-existent adsorption at higher pH values as well 233 as the negative impact of higher ionic strengths as both parameters cause unfavorable 234 adsorption conditions due to decreasing positive surface charges and competition effects.

235 When interpreting these adsorption data, it must be taken into account that the used magnetite 236 phase was partly oxidized to maghemite in its near-surface region under the prevailing oxic 237 conditions. However, comparison of Se adsorption studies on magnetite and maghemite reveals 238 that both minerals behave very much alike. The adsorption capacity of both maghemite and 239 magnetite is similar in terms of its dependence on Se speciation, pH or ionic strength (Jordan 240 et al., 2013; Jordan et al., 2014). Interesting is also that several previous Se adsorption studies 241 on magnetite led to similar results regardless of whether the experiments were performed under 242 oxic (Martínez et al., 2006) or anoxic conditions (Loyo et al., 2008; Jordan et al., 2009; Kim et 243 al., 2012). In comparative studies Missana et al. (2009) proved that no differences in terms of 244 selenite sorption occurred under oxic and anoxic conditions. Furthermore, it is not always 245 documented to what extent the synthesized, industrially-produced or natural magnetite tested 246 in the above mentioned sorption studies might also have been affected by a partial oxidation 247 into maghemite. In contrast, magnetite synthesized under well controlled, anoxic conditions 248 proved to be a very effective reducer for selenite {Scheinost, 2008 #139;Scheinost, 2008 #266}.

249 **3.2** Effects of selenium adsorption on the properties of the solid phase

To assess the impact of selenite or selenate adsorption on the properties of the magnetite phase, selected samples from adsorption experiments were characterized by various solids analysis methods. A detailed description and evaluation of these analyses can be found in the ESI chapter 3.1. In short, XRD and SEM/EDX analyses demonstrated that neither the mineralogical composition (ESI Fig. A.3) nor the morphology (Fig. 3) of the initial magnetite nanoparticles was affected by the adsorption of selenite or selenate respectively. EDXRF data (ESI Table A.1) and SEM/EDX analysis (ESI Fig. A.4), however, proved that the examined solid samples

contained significant Se quantities after adsorption, whose proportions depend on the initial Se
speciation and concentration. For a solid sample from the selenite system, with a relatively high
total Se amount of 4,200 ppm, the oxidation state of this Se proportion was identified by XPS
as Se(IV) (ESI Table A.2), demonstrating that the retention of selenite is not accompanied by a
change of the Se oxidation state.

Furthermore, XPS analysis and the comparison of the Fe(II)/Fe_{total} ratio of the solids before and after the adsorption of selenite or selenate yielded to comparable results (ESI Table A.2). This observation that the oxidation of magnetite to maghemite is not progressing significantly during the oxic adsorption experiments, can be explained by the formation of an initial maghemite oxidation layer that prevents the underlying magnetite core from further aerial oxidation (He and Traina, 2005; Rebodos and Vikesland, 2010; Khan et al., 2015).



268

 $\begin{array}{ll} 269 \\ 270 \end{array} \quad \begin{array}{l} \mbox{Fig. 3: SEM results of magnetite samples from selenite and selenate adsorption studies; c(Se)_0 = 5 \times 10^{-3} \\ \mbox{mol/L.} \end{array}$

271

272 **3.3** Characterization of the adsorption complexes

Se K-edge XAFS analysis was used to characterize the oxidation state (XANES) as well as the local structure (EXAFS) of the immobilized Se. For this purpose, magnetite samples from selenite or selenate adsorption experiments conducted at pH 4, 7 and 9.2 were analyzed in order to investigate the influence of pH on the sorption mechanism.

Unfortunately, even at pH 4, selenate sorption on magnetite was too low to be analyzed by XAFS spectroscopy. A determination of the specific adsorption mechanisms was therefore not possible in case of the selenate system. However, the low retention capacity in combination with the negative impact of higher ionic strengths and pH values generally points to the formation of outer-sphere adsorption complexes. That selenate oxyanions form primarily outersphere complexes in contact to iron (hydr)oxides was previously shown for maghemite (Jordan et al., 2013) and hematite (Börsig et al., 2017) by XAFS, as well as by SCM for magnetite (Martínez et al., 2006). It should be noted, however, that the observed dependency on ionic strength and pH alone is not an unambiguous characteristic in favor of an outer-sphere selenate adsorption (Su and Suarez, 2000).

287 Unlike the samples from the selenate systems, the selenite samples had taken up enough Se to 288 be analyzed by XAFS analysis. Fig. 4 shows the Se K-edge XANES spectra of the analyzed 289 samples from the selenite system together with reference spectra of Se(IV) (Na₂SeO₄ solution) 290 and Se(0) (grey elemental Se) compounds. For all three samples, the adsorption edge exactly 291 matches that of the Se(IV) reference spectra (12.660 KeV), indicating that the initial tetravalent 292 oxidation state remained unchanged. XANES data are thus in line with the XPS results which 293 showed that the adsorption processes caused neither selenite reduction nor oxidation. An 294 immobilization due to selenite reduction and formation of sparingly soluble reduced Se 295 compounds such as elemental Se⁰ or selenide minerals can therefore be excluded not only at 296 alkaline but also at acidic pH conditions. It is known that in anoxic systems reduction of selenite 297 oxyanions by Fe(II)-bearing minerals like magnetite is generally possible (Scheinost et al., 298 2008; Scheinost and Charlet, 2008; Börsig et al., 2018). However, even in an anoxic 299 environment, selenite reduction does not inevitably take place, as other selenite-magnetite 300 adsorption studies have proven (Loyo et al., 2008; Jordan et al., 2009; Missana et al., 2009). 301 The exact reasons for this are unclear, but several possible explanations have been discussed in 302 previous studies. According to Loyo et al. (2008), one reason could be the slow reaction time 303 of the selenite reduction process. However, a direct comparison of the reaction times used in 304 the above mentioned studies, ranging from a few hours to 30 days, is difficult because of the 305 partially very different experimental setups (i.e. initial Se concentrations, magnetite amounts, 306 pH, presence of secondary ions, etc.). For this reason, the reaction time must rather be seen in 307 relation to the respective mineral surface coverage and reduction kinetics. According to 308 Missana et al. (2009), reduction of selenite oxyanions is only possible if the selenite surface 309 coverage of the corresponding Fe(II)-bearing mineral phase is relatively low, as high coverages 310 slow down electron transfer processes. This theory, however, has not yet been experimentally 311 proven. Furthermore, the presence or absence of Se reduction processes could be affected by 312 the specific Fe(II)/Fe(III) ratio of the magnetite phase, since the magnetite stoichiometry 313 strongly influences its physicochemical properties, including the sorption capacity and the 314 reduction potential (Gorski and Scherer, 2010). Higher Fe(II) fractions have a positive impact 315 on the reduction potential of magnetite, which was proven in sorption studies with uranium 316 (Latta et al., 2012) and neptunium (Wylie et al., 2016), among others.



- 317
- 318

319
320Fig. 4: Se K-edge XANES spectra of Se references and magnetite samples from selenite adsorption studies
performed at different pH values; $c(Se)_0 = 10^{-3} \text{ mol/L}$.

321 To identify the specific adsorption type, the samples were analyzed by Se K-edge EXAFS 322 spectroscopy (Fig. 4). The k³-weighted spectra were fit with a FEFF 8.2 file generated with the 323 crystallographic structure of mandarinoite $(Fe_2(SeO_3)_3 \cdot 6H_2O, CIF 0005198, Hawthorne,$ 1984). For all three selenite sorption samples, the EXAFS Fourier transforms (FT) are 324 325 dominated by a strong peak at 1.35 Å (uncorrected for phase shift). Responsible for this peak 326 is the oxygen coordination shell. The fit of this shell using a single scattering Se-O path resulted 327 in coordination number (CN) of 2.8 and atomic distances of 1.70–1.71 Å (Table 1), confirming 328 the tetravalent oxidation state and the unchanged pyramidal-shaped molecular structure of the 329 selenite oxyanion. Beyond the oxygen coordination shell, a small double peak arises in the range 2.3–3.5 Å (uncorrected for phase shift), with the relative ratio of the two peaks changing 330 331 with pH: For the sample representing acidic conditions [Se(IV)AdsMt-pH4], the right-side peak 332 at 2.9 Å dominates, whereas under alkaline conditions [Se(IV)AdsMt-pH9.2] the left-side peak 333 at 2.6 Å becomes more pronounced. In addition, the peak intensities at alkaline pH are generally 334 lower than for acidic conditions. The peaks could be fitted with two individual single scattering Se-Fe paths, providing between 0.3–0.9 Fe atoms at an atomic distance of 2.90–2.93 Å, and 335

- 336 0.4–0.9 Fe atoms at an atomic distance of 3.37–3.40 Å (Table 1). Note that the Debye-Waller
- factors of both Se-Fe paths were kept correlated, to achieve a satisfying fitting of those peaks.
- 338 The graphical representation of the fit results can be found in ESI Fig. A.5.

Table 1: Se-K XANES edge energies and EXAFS fit results of selenite-magnetite adsorption samples $(S_0^2 = 0.9)$.

		Oxygen shell		Iron shells					
Sample	E₀ [keV]	CN ^a	R [Å] ⁵	σ² [Ų] ^c	CN	R [Å]	σ² [Ų]	ΔE₀ [eV]	χ _{res} [%]
Se(IV)AdsMt-pH4	12.6600	0.9 O	2.8	1.70	0.9 F	e 2.93	0.0093 ^d	14.8	12.5
					1.7 F	e 3.40	0.0093 ^d		
Se(IV)AdsMt-pH7	12.6595	0.9 O	2.8	1.70	0.5 F	e 2.93	0.0048 ^d	15.4	13.4
					0.6 F	e 3.39	0.0048 ^d		
Se(IV)AdsMt-pH9	12.6596	0.9 O	2.8	1.71	0.3 F	e 2.90	0.0030 ^d	15.7	14.6
					0.4 F	e 3.37	0.0030 ^d		

^a CN: coordination number, error ± 25%. ^b R: radial distance, error ± 0.01 Å. ^c σ^2 : Debye-Waller factor, error ± 0.0005 Å². ^d correlated σ^2 .

341 Although the necessity for such relatively small coordination numbers may be questioned at

342 first due to their inevitably larger error, the use of two scattering paths was required to achieve

343 stable fitting results. Contrary to this, the use of only one Se-Fe path or a mixture of Se-Fe and

344 Se-O paths led to poor fitting results. Furthermore, data of other studies (Missana et al., 2009;

Jordan et al., 2014) as well as the results of principal component analysis (see chapter 3.4)

346 support this assumption.



Fig. 5: Model showing the structure of (a) ${}^{2}E$ and (b) ${}^{2}C$ adsorption complexes between selenite molecules and FeO₆ octahedra.

The occurrence of Fe atoms in the second shell indicate an inner-sphere bonding between the selenite oxyanion and the mineral surface. The shorter Fe shell with a distance of 2.90-2.93 Å points to the formation of a bidentate mononuclear edge-sharing ²E arrangement. As shown in Fig. 5a, ²E adsorption complexes are characterized by two oxygen atoms of the selenite molecule simultaneously forming the edge of an FeO₆ octahedron on the iron (hydr)oxide surface. The longer Fe shell, on the other hand, represents bidentate binuclear corner-sharing ²C adsorption complexes, where one adsorbed selenite molecule is attached to two FeO₆ octahedra (Fig. 5b). That the interaction of selenite oxyanions with iron (hydr)oxides can cause the (simultaneous) formation of these types of inner-sphere adsorption complexes, was also demonstrated by several previous studies (Hayes et al., 1987; Manceau and Charlet, 1994; Hiemstra et al., 2007; Missana et al., 2009; Jordan et al., 2014; Börsig et al., 2017).

370 According to the EXAFS results, other types of sorption or retention mechanisms can be 371 excluded. For instance, Missana et al. (2009) reported formation of a discrete ferric selenite 372 phase like $Fe_2(SeO_3)_3 \cdot 6H_2O$ at pH 4. This would results in higher Fe coordination numbers as 373 well as in the presence of additional Se backscatter atoms, which are both missing in our 374 EXAFS data. Also the formation of monodentate mononuclear corner-sharing ¹V complexes, 375 which can arise for instance during the adsorption of As-oxyanions (arsenate or arsenite) on magnetite or maghemite can be ruled out (Morin et al., 2008; Zhang et al., 2011; Navarathna et 376 al., 2019), since structural features in the EXAFS FT range beyond 3.5 Å are absent. 377 378 Furthermore, we could exclude the presence of tridentate hexanuclear corner-sharing ${}^{3}C$ 379 complexes, that have been shown to form with the oxyanions arsenite (Wang et al., 2008; Liu et al., 2015) and antimonite (Kirsch et al., 2008) at the {111} faces of magnetite, since 380 14

381 backscatterer atoms at higher atomic distances are absent. This assumption is supported by

- 382 results of previous studies, in which also no hints for selenite ¹V or ³C adsorption complexes
- 383 on magnetite or maghemite have been found (Missana et al., 2009; Jordan et al., 2014). Jordan
- 384 et al. (2014) explain this different behavior of selenite compared to arsenite or antimonite by
- the different sizes of these trigonal pyramidal oxyanion molecules.

386 **3.4** Properties and stability of the selenite surface complexes

387 Based on XAFS data, interaction of dissolved selenite with magnetite under oxic conditions 388 leads to the simultaneous formation of ${}^{2}E$ and ${}^{2}C$ adsorption complexes. Which types of 389 adsorption complexes develop on a particular material generally depends on the prevailing 390 hydrochemical conditions and the structural and morphological properties of the adsorbent 391 phase. This can be explained by the atomic structure and features of specific crystal surfaces. 392 Due to the distinct arrangement of functional surface groups or, respectively, adsorption sites, 393 certain types of adsorption complexes occur mainly on certain crystal surfaces. Since the 394 affinity of an adsorbate for certain adsorption sites is determined among other things by its 395 general surface coverage (Peak and Sparks, 2002; Fukushi and Sverjensky, 2007), which in turn 396 is influenced by the pH value, different crystal surfaces show different reactivities depending 397 on the degree of coverage or pH. In case of oxyanion adsorption on magnetite, formation of ${}^{2}C$ 398 adsorption complexes is mainly associated with the $\{100\}$ crystal surface, while the ²E 399 complexes are related to the {110} or {111} facets (Jönsson and Sherman, 2008; Wang et al., 400 2008; Wang et al., 2011; Liu et al., 2015; Navarathna et al., 2019).

401 Changing selenite adsorption types depending on the solution pH were determined by EXAFS 402 analysis for both magnetite (Missana et al., 2009) and maghemite (Jordan et al., 2014). The 403 respective results indicate that ${}^{2}E$ and ${}^{2}C$ selenite adsorption complexes appear simultaneously 404 at acidic conditions or at high surface coverages, respectively, with the corner-sharing ²C 405 complexes being dominant. With increasing pH values or decreasing surface coverages, the 406 share of ²C complexes tends to decrease and at alkaline conditions (>pH 8) only edge-sharing 407 2 E adsorption complexes occur. However, the authors of both studies noted that the evaluation 408 of EXAFS data for such samples is quite difficult. Due to the small coordination numbers, 409 especially at neutral or alkaline conditions, identification of the adsorption complexes as well 410 as determination of their relative shares becomes more and more challenging. This challenge 411 also arises for the EXAFS data of this work. Particularly the samples at pH 7 and pH 9.2 are 412 characterized by small Fe coordination numbers, which makes it difficult to estimate their 413 relative fractions.

We therefore performed a statistical analysis of the EXAFS spectra with Iterative Transformation Factor Analysis (ITFA) (Rossberg et al., 2003). ITFA allows determining the number of principal components (PC) and their respective factor loadings. Fig. 6a illustrates the good match between the experimental spectra (black) and their reconstructions (red lines) by two PC. The ITFA thus confirms that two individual spectral components are needed to characterize the EXAFS spectra of all three adsorption samples.

420 Moreover, the corresponding Varimax factor loadings (Fig. 6b) show that the sample at pH 4 421 is solely dominated by PC 1, whereas PC 2 primarily represents selenite adsorption under 422 alkaline conditions. Based on the previous observations and the findings of Missana et al. 423 (2009) and Jordan et al. (2014), these results can be interpreted in a way that the different factor 424 loadings are associated with a varying distribution of ²E and ²C surface adsorption complexes. Accordingly, PC 1 reflects a combination of ²E and ²C adsorption complexes with a higher 425 426 proportion of corner-sharing ²C complexes, while PC 2 represents a mixture of both 427 complexation types with a higher share of ${}^{2}E$ complexes. Under neutral or slightly alkaline 428 conditions, both adsorption types would thus occur in approximately equal proportions, which 429 is consistent with the factor loading of sample Se(IV)AdsMt-pH7.



⁴³¹

Fig. 6: (a & b) Se K-edge EXAFS spectra of magnetite samples from selenite adsorption studies performed
 at different pH values (blue lines) and their reconstruction by two factors (red lines). (c) Varimax loadings
 of the two factors.

The dependency of the complexation type from the pH value can basically be interpreted that increasing pH values and a higher negative surface charge cause a change in the stability and

thus in the prevailing dominance of the selenite adsorption complexes. Under favorable adsorption conditions, the affinity of selenite oxyanions to form corner-sharing ²C complexes is generally higher than for the edge-sharing ²E complexes, leading to a quantitatively predominant of the ²C complexes over a wide pH range. However, at more alkaline conditions, which are generally unfavorable for selenite adsorption, the ²E complexes become more stable. This effect leads to a significant increase in the proportion of ²E over ²C complexes, although the absolute amount of adsorbed selenite decreases with increasing pH.

444 **4** Conclusion

445 When redox-sensitive materials are considered to prevent the migration of pollutants, it must 446 be taken into account that the retention properties of these materials can change considerably 447 in natural environments. This study demonstrates that magnetite nanoparticles can effectively 448 remediate selenite and selenate contaminated wastewaters even if they are oxidized. However, 449 the retention requires suitable hydrochemical conditions, which mainly concern the prevailing 450 pH and the corresponding selenium speciation. While retention of selenate only takes place at 451 acidic conditions, selenite is immobilized over a large pH range. No reduction processes were 452 involved in the selenium immobilization. The specific retention mechanism are attributable to 453 the formation of surface adsorption complexes. A mixture of mononuclear edge-sharing (^{2}E) 454 and binuclear corner-sharing (^{2}C) inner-sphere complexes in case of selenite and most likely 455 outer-sphere surface complexes in case of selenate. It was found that both types of inner-sphere 456 selenite complexes have different affinities and stabilities depending on the solution pH.

457 Regarding the assessment of the remediation efficiencies of oxidized magnetite, the results 458 show that the mechanisms of selenate and selenate adsorption are comparable to the findings 459 from previous adsorption studies on pure maghemite. Accordingly, in systems where no 460 reduction takes place, partially oxidized magnetite nanoparticles can approximately be 461 considered as a maghemite-like adsorbent phase. These findings help to better understand the 462 retention behavior of selenium oxyanions in contact with nanoparticulate magnetite/maghemite 463 phases under oxic conditions and could be used in modeling the migration of selenium 464 oxyanions in subsurface environments.

465 Conflicts of interest

466 There are no conflicts of interest to declare.

467 Acknowledgements

This work is part of the *IMMORAD* project, funded by the German Federal Ministry for Education and Research (BMBF) under grant No. 02NUK019B. Additional financial support was provided by the Graduate School for Climate and Environment (GRACE) at KIT. The authors would like to thank Dr. Peter Weidler and Volker Zibat for BET and SEM analyses. We also thank Dr. Utz Kramar and Claudia Mößner for their help with XRF and ICP-MS analyses. The ESRF and the team of the Rossendorf Beamline (BM 20) are gratefully acknowledged for the provision of beam time and their support during the XAFS measurements.

475 **References**

- Ankudinov A. L. and Rehr J. J. (1997) Relativistic calculations of spin-dependent x-ray-absorption
 spectra. *Phys. Rev. B* 56, 1712–1715.
- Bingham P. A., Connelly A. J., Cassingham N. J. and Hyatt N. C. (2011) Oxidation state and local
 environment of selenium in alkali borosilicate glasses for radioactive waste immobilisation. *J. Non. Cryst. Solids* 357, 2726–2734.
- Börsig N., Scheinost A. C., Shaw S., Schild D. and Neumann T. (2018) Retention and multiphase
 transformation of selenium oxyanions during the formation of magnetite via iron(ii) hydroxide and
 green rust. *Dalt. Trans.* 47, 11002–11015.
- Börsig N., Scheinost A. C., Shaw S., Schild D. and Neumann T. (2017) Uptake mechanisms of selenium
 oxyanions during the ferrihydrite-hematite recrystallization. *Geochim. Cosmochim. Acta* 206, 236–253.
- 487 De Cannière P., Maes A., Williams S., Bruggeman C., Beauwens T., Maes N. and Cowper M. (2010)
 488 Behaviour of Selenium in Boom Clay. External Report of the Belgian Nuclear Research Centre.,
 489 SCK•CEN-ER-120, Mol, BEL.
- Chan Y. T., Kuan W. H., Chen T. Y. and Wang M. K. (2009) Adsorption mechanism of selenate and selenite on the binary oxide systems. *Water Res.* 43, 4412–4420.
- Chowdhury S. R. and Yanful E. K. (2010) Arsenic and chromium removal by mixed magnetitemaghemite nanoparticles and the effect of phosphate on removal. *J. Environ. Manage.* 91, 2238–
 2247.
- 495 Cornell R. M. and Schwertmann U. (2003) *The iron oxydes: Structure, Properties, Reactions,* 496 *Occurences and Uses.* 2nd ed., Wiley-VCH, Weinheim, Germany.
- 497 Dhillon K. S. and Dhillon S. K. (2003) Distribution and management of seleniferous soils. *Adv. Agron.*498 79, 119–184.
- Duc M., Lefèvre G., Fédoroff M., Jeanjean J., Rouchaud J. C., Monteil-Rivera F., Dumonceau J. and
 Milonjic S. (2003) Sorption of selenium anionic species on apatites and iron oxides from aqueous
 solutions. J. Environ. Radioact. 70, 61–72.
- Fernández-Martínez A. and Charlet L. (2009) Selenium environmental cycling and bioavailability: A
 structural chemist point of view. *Rev. Environ. Sci. Biotechnol.* 8, 81–110.
- Frechou C., Aguerre S., Degros J. P., Kerlau G. and Grangeon T. (2007) Improvement of a radiochemical separation for selenium 79: Applications to effluents and nuclear wastes. *Talanta* 72, 1166–1171.

- Fukushi K. and Sverjensky D. A. (2007) A surface complexation model for sulfate and selenate on iron
 oxides consistent with spectroscopic and theoretical molecular evidence. *Geochim. Cosmochim.* Acta 71, 1–24.
- Génin J.-M. R., Ruby C., Géhin A. and Refait P. (2006) Synthesis of green rusts by oxidation of
 Fe(OH)₂, their products of oxidation and reduction of ferric oxyhydroxides; Eh-pH Pourbaix
 diagrams. *Comptes Rendus Geosci.* 338, 433–446.
- Gorski C. A. and Scherer M. M. (2010) Determination of nanoparticulate magnetite stoichiometry by
 Mössbauer spectroscopy, acidic dissolution, and powder X-ray diffraction: A critical review. Am.
 Mineral. 95, 1017–1026.
- 516 Hawthorne F. C. (1984) The crystal structure of mandarinoite, $Fe^{3+}_{2}Se_{3}O_{9} \cdot 6H_{2}O$. *Can. Mineral.* **22**, 475– 517 480.
- Hayes K. F., Roe A. L., Brown G. E., Hodgson K. O., Leckie J. O. and Parks G. A. (1987) In Situ Xray Absorption Study of Surface Complexes: Selenium Oxyanions on α-FeOOH. Science (80-.).
 238, 783–786.
- He Y. T. and Traina S. J. (2005) Cr(VI) reduction and immobilization by magnetite under alkaline pH
 conditions: The role of passivation. *Environ. Sci. Technol.* 39, 4499–4504.
- Hiemstra T., Rietra R. P. J. J. and Van Riemsdijk W. H. (2007) Surface Complexation of Selenite on
 Goethite: MO/DFT Geometry and Charge Distribution. *Croat. Chem. Acta* 80, 313–324.
- Horst M. F., Lassalle V. and Ferreira M. L. (2015) Nanosized magnetite in low cost materials for
 remediation of water polluted with toxic metals, azo- and antraquinonic dyes. *Front. Environ. Sci. Eng.* 9, 746–769.
- Hu J. D., Zevi Y., Kou X. M., Xiao J., Wang X. J. and Jin Y. (2010) Effect of dissolved organic matter
 on the stability of magnetite nanoparticles under different pH and ionic strength conditions. *Sci. Total Environ.* 408, 3477–3489.
- Iwatsuki M. and Fukasawa T. (1993) Nondestructive and Complete Analysis of Magnetite-Maghemite
 Solid Solutions by a Combined X-Ray Diffraction/Fluorescence Method. *Anal. Sci.* 9, 95–98.
- Jönsson J. and Sherman D. M. (2008) Sorption of As(III) and As(V) to siderite, green rust (fougerite)
 and magnetite: Implications for arsenic release in anoxic groundwaters. *Chem. Geol.* 255, 173–
 181.
- Jordan N., Lomenech C., Marmier N., Giffaut E. and Ehrhardt J.-J. (2009) Sorption of selenium(IV)
 onto magnetite in the presence of silicic acid. J. Colloid Interface Sci. 329, 17–23.
- Jordan N., Ritter A., Foerstendorf H., Scheinost A. C., Weiß S., Heim K., Grenzer J., Mücklich A. and
 Reuther H. (2013) Adsorption mechanism of selenium(VI) onto maghemite. *Geochim. Cosmochim. Acta* 103, 63–75.
- Jordan N., Ritter A., Scheinost A. C., Weiss S., Schild D. and Hübner R. (2014) Selenium(IV) uptake
 by maghemite (γ-Fe₂O₃). *Environ. Sci. Technol.* 48, 1665–1674.
- Khan U. S., Amanullah, Manan A., Khan N., Mahmood A. and Rahim A. (2015) Transformation
 mechanism of magnetite nanoparticles. *Mater. Sci. Pol.* 33, 278–285.
- Kim S. S., Min J. H., Lee J. K., Baik M. H., Choi J.-W. and Shin H. S. (2012) Effects of pH and anions
 on the sorption of selenium ions onto magnetite. *J. Environ. Radioact.* 104, 1–6.
- Kirsch R., Scheinost A. C., Rossberg A., Banerjee D. and Charlet L. (2008) Reduction of antimony by
 nano-particulate magnetite and mackinawite. *Mineral. Mag.* 72, 185–189.
- Kuhn L. T., Bojesen A., Timmermann L., Nielsen M. M. and Mørup S. (2002) Structural and magnetic
 properties of core-shell iron-iron oxide nanoparticles. J. Phys. Condens. Matter 14, 13551–13567.

- Kuppusamy S., Palanisami T., Megharaj M., Venkateswarlu K. and Naidu R. (2016) In-Situ
 Remediation Approaches for the Management of Contaminated Sites: A Comprehensive
 Overview. In *Reviews of Environmental Contamination and Toxicology Volume 236* (ed. P. de
 Voogt). Springer International Publishing, Cham. pp. 1–115.
- Latta D. E., Gorski C. A., Boyanov M. I., O'Loughlin E. J., Kemner K. M. and Scherer M. M. (2012)
 Influence of Magnetite Stoichiometry on U^{VI} reduction. *Environ. Sci. Technol.* 46, 778–786.
- Lemly A. D. (2004) Aquatic selenium pollution is a global environmental safety issue. *Ecotoxicol. Environ. Saf.* 59, 44–56.
- Lenz M. and Lens P. N. L. (2009) The essential toxin: The changing perception of selenium in environmental sciences. *Sci. Total Environ.* 407, 3620–3633.
- Li Z., Liu M., Chen L. K. and Li G. Z. (2017) Combined Toxicity of an Environmental Remediation
 Residue, Magnetite Fe₃O₄ Nanoparticles/Cr(VI) Adduct. *Biomed. Environ. Sci.* **30**, 783–791.
- Liu A., Liu J., Pan B. and Zhang W. X. (2014) Formation of lepidocrocite (γ-FeOOH) from oxidation
 of nanoscale zero-valent iron (nZVI) in oxygenated water. *RSC Adv.* 4, 57377–57382.
- Liu C. H., Chuang Y. H., Chen T. Y., Tian Y., Li H., Wang M. K. and Zhang W. (2015) Mechanism of
 Arsenic Adsorption on Magnetite Nanoparticles from Water: Thermodynamic and Spectroscopic
 Studies. *Environ. Sci. Technol.* 49, 7726–7734.
- Loyo R. L. de A., Nikitenko S. I., Scheinost A. C. and Simonoff M. (2008) Immobilization of selenite
 on Fe₃O₄ and Fe/Fe₃C ultrasmall particles. *Environ. Sci. Technol.* 42, 2451–2456.
- Manceau A. and Charlet L. (1994) The Mechanism of Selenate Adsorption on Goethite and Hydrous
 Ferric Oxide. J. Colloid Interface Sci. 168, 87–93.
- Martínez M., Giménez J., de Pablo J., Rovira M. and Duro L. (2006) Sorption of selenium(IV) and
 selenium(VI) onto magnetite. *Appl. Surf. Sci.* 252, 3767–3773.
- Milonjić S. K., Kopečni M. M. and Ilić Z. E. (1983) The point of zero charge and adsorption properties
 of natural magnetite. *J. Radioanal. Chem.* 78, 15–24.
- Missana T., Alonso U., Scheinost A. C., Granizo N. and García-Gutiérrez M. (2009) Selenite retention
 by nanocrystalline magnetite: Role of adsorption, reduction and dissolution/co-precipitation
 processes. *Geochim. Cosmochim. Acta* 73, 6205–6217.
- Morin G., Ona-Nguema G., Wang Y., Menguy N., Juillot F., Proux O., Guyot F., Calas G. and Brown
 G. E. (2008) Extended X-ray absorption fine structure analysis of arsenite and arsenate adsorption
 on maghemite. *Environ. Sci. Technol.* 42, 2361–2366.
- 582 Mu Y., Jia F., Ai Z. and Zhang L. (2017) Iron oxide shell mediated environmental remediation properties
 583 of nano zero-valent iron. *Environ. Sci. Nano* 4, 27–45.
- Munier-Lamy C., Deneux-Mustin S., Mustin C., Merlet D., Berthelin J. and Leyval C. (2007) Selenium
 bioavailability and uptake as affected by four different plants in a loamy clay soil with particular
 attention to mycorrhizae inoculated ryegrass. J. Environ. Radioact. 97, 148–158.
- Nakamaru Y. M. and Altansuvd J. (2014) Speciation and bioavailability of selenium and antimony in
 non-flooded and wetland soils: A review. *Chemosphere* 111, 366–371.
- Navarathna C. M., Karunanayake A. G., Gunatilake S. R., Pittman C. U., Perez F., Mohan D. and Mlsna
 T. (2019) Removal of Arsenic(III) from water using magnetite precipitated onto Douglas fir
 biochar. J. Environ. Manage. 250, 109429.
- 592 Peak D. and Sparks D. L. (2002) Mechanisms of selenate adsorption on iron oxides and hydroxides.
 593 Environ. Sci. Technol. 36, 1460–1466.
- 594 Rebodos R. L. and Vikesland P. J. (2010) Effects of oxidation on the magnetization of nanoparticulate

- 595 magnetite. *Langmuir* **26**, 16745–16753.
- Ressler T. (1998) WinXAS: a program for X-ray absorption spectroscopy data analysis under MS Windows. J. Synchrotron Radiat. 5, 118–122.
- Rietra R. P. J. J., Hiemstra T. and van Riemsdijk W. H. (2001) Comparison of Selenate and Sulfate
 Adsorption on Goethite. J. Colloid Interface Sci. 240, 384–390.
- Rossberg A., Reich T. and Bernhard G. (2003) Complexation of uranium(VI) with protocatechuic acid application of iterative transformation factor analysis to EXAFS spectroscopy. *Anal. Bioanal. Chem.* 376, 631–638.
- Rovira M., Giménez J., Martínez M., Martínez-Lladó X., de Pablo J., Martí V. and Duro L. (2008)
 Sorption of selenium(IV) and selenium(VI) onto natural iron oxides: Goethite and hematite. *J. Hazard. Mater.* 150, 279–284.
- Salah S. and Wang L. (2014) Speciation and solubility calculations for waste relevant radionuclides in
 Boom Clay. External Report of the Belgian Nuclear Research Centre., SCK•CEN-ER-198, Mol,
 BEL.
- Salazar Camacho C. A. and Villalobos Peñalosa M. (2017) Characterization and surface reactivity of
 natural and synthetic magnetites: II. adsorption of Pb(II) and Zn(II). *Rev. Int. Contam. Ambient.*33, 165–176.
- Scheinost A. C. and Charlet L. (2008) Selenite reduction by mackinawite, magnetite and siderite: XAS
 characterization of nanosized redox products. *Environ. Sci. Technol.* 42, 1984–1989.
- Scheinost A. C., Kirsch R., Banerjee D., Fernandez-Martinez A., Zaenker H., Funke H. and Charlet L.
 (2008) X-ray absorption and photoelectron spectroscopy investigation of selenite reduction by
 FeII-bearing minerals. J. Contam. Hydrol. 102, 228–245.
- 617 Schwaminger S. P., Bauer D., Fraga-García P., Wagner F. E. and Berensmeier S. (2017) Oxidation of 618 magnetite nanoparticles: impact on surface and crystal properties. *CrystEngComm* **19**, 246–255.
- Séby F., Potin-Gautier M., Giffaut E., Borge G. and Donard O. F. X. (2001) A critical review of
 thermodynamic data for selenium species at 25°C. *Chem. Geol.* 171, 173–194.
- Sharifi Dehsari H., Ksenofontov V., Möller A., Jakob G. and Asadi K. (2018) Determining
 Magnetite/Maghemite Composition and Core-Shell Nanostructure from Magnetization Curve for
 Iron Oxide Nanoparticles. J. Phys. Chem. C 122, 28292–28301.
- Signorini L., Pasquini L., Savini L., Carboni R., Boscherini F., Bonetti E., Giglia A., Pedio M., Mahne
 N., Mahne N., Nannarone S. and Nannarone S. (2003) Size-dependent oxidation in iron/iron oxide
 core-shell nanoparticles. *Phys. Rev. B Condens. Matter Mater. Phys.* 68, 1–8.
- Su C. and Suarez D. L. (2000) Selenate and Selenite Sorption on Iron Oxides. Soil Sci. Soc. Am. J. 64, 101–111.
- Tan L. C., Nancharaiah Y. V., van Hullebusch E. D. and Lens P. N. L. (2016) Selenium: environmental
 significance, pollution, and biological treatment technologies. *Biotechnol. Adv.* 34, 886–907.
- Usman M., Byrne J. M., Chaudhary A., Orsetti S., Hanna K., Ruby C., Kappler A. and Haderlein S. B.
 (2018) Magnetite and Green Rust: Synthesis, Properties, and Environmental Applications of Mixed-Valent Iron Minerals. *Chem. Rev.* 118, 3251–3304.
- Wang Y., Morin G., Ona-Nguema G., Juillot F., Calas G. and Brown G. E. (2011) Distinctive arsenic(V)
 trapping modes by magnetite nanoparticles induced by different sorption processes. *Environ. Sci. Technol.* 45, 7258–7266.
- Wang Y., Morin G., Ona-Nguema G., Menguy N., Juillot F., Aubry E., Guyot F., Calas G. and Brown
 G. E. (2008) Arsenite sorption at the magnetite-water interface during aqueous precipitation of
 magnetite: EXAFS evidence for a new arsenite surface complex. *Geochim. Cosmochim. Acta* 72,

640 2573–2586.

- Weidner E. and Ciesielczyk F. (2019) Removal of hazardous oxyanions from the environment using
 metal-oxide-based materials. *Materials (Basel)*. 16.
- Wilkin R. T., Su C., Ford R. G. and Paul C. J. (2005) Chromium-removal processes during groundwater
 remediation by a zerovalent iron permeable reactive barrier. *Environ. Sci. Technol.* 39, 4599–4605.
- Wylie E. M., Olive D. T. and Powell B. A. (2016) Effects of Titanium Doping in Titanomagnetite on
 Neptunium Sorption and Speciation. *Environ. Sci. Technol.* 50, 1853–1858.
- Kang M., Pan G., Zhao D. and He G. (2011) XAFS study of starch-stabilized magnetite nanoparticles
 and surface speciation of arsenate. *Environ. Pollut.* 159, 3509–3514.
- 649